

# GETIG 309L

## IDENTIFICATION: ER 309L

**SPECIFICATIONS:** AWS A 5.9: ER309L, BS2901-90 309S92,  
DIN 8556-86 WSGX2CrNi 24.12

### CHARACTERISTICS:

Solid wire deposits a 24 % Cr / 13 % Ni austenitic stainless steel weld metal with a ferrite content about FN 12. The high alloy level and high ferrite content enables the weld metal to tolerate dilution from carbon and low alloy steels without hot cracking. Deposited weld metal is of radiographic quality.

### APPLICATIONS:

- Buffer layer on mild steel or low alloy steels.
- Joining of clad steels and dissimilar joints between stainless and mild or low alloy steels. Joining of ferrite-martensitic stainless steels.
- Welding of similar composition, 309 type stainless steel.
- Joining type 304/304L, 347, 321, 316/316L and duplex stainless steel to mild and low alloy steels.

**SHIELDING GAS:** Argon 99.99% 6-12 l/min.

**FERRITE CONTENT IN THE WELD METAL:** 8 – 16 FN.

**WELDING CURRENT:** DC(-)

### CORROSION RESISTANCE:

Good resistance to general and intergranular corrosion. Also good resistance to oxidising acids and cold reducing acids.

### COMPOSITION OF THE WIRE (RANGE) %

C	Mn	Si	Cr	Cu
0.03 max	1.0-2.5	0.30-0.65	23.0-25.0	0.50 max
Ni	Mo	S	P	
12-14	0.50 max	0.03 max	0.03 max	

### MECHANICAL PROPERTIES (RANGE)

UTS (MPa)	YS (MPa)	ELN % (L=4D)	CVN impact Strength	
			Temp 0°C	Joules
540-650	380-480	35-45		50-100

### RECOMMENDED CURRENT AND PACKING DATA

SIZE (mm)	LENGTH (mm)	PACKING/BOX
1.6	1000	5 x 4 = 20 Kg
2.0	1000	5 x 4 = 20 Kg
2.4	1000	5 x 4 = 20 Kg
3.15	1000	5 x 4 = 20 Kg

## Manufactured by: GEE LIMITED

Regd. Off & Works: plot No.B - 12, MIDC, Kalyan-Bhiwandi Road, Saravli, Kalyan (West)  
Thane, Maharashtra, India.  
Website: www.geelimited.com

## Authorised Distributor: CROSS MARKETING

Head Office: Martin Burn Business Park | Suite No 900A | Block- BP | Salt Lake | Sector - V | Kolkata - 700091 | West Bengal | India  
Ph: (+91) 9163763419 | (+91) 9038320189  
Email: lakhotia.ravi@gmail.com | crossmarketingkolkata@gmail.com