

FW 2209

CODIFICATION:

AWS : SFA 5.9 ER2209
EN ISO: 14343-A W 22 9 3 NL

CHARACTERISTICS AND APPLICATIONS:

FW 2209 is a solid wire for TIG welding, available in bright finish, gives smooth flow, stable arc and spatter free under optimum welding conditions. It gives radiographic quality weld deposit. Deposits have duplex microstructures consisting of an austenite – ferrite matrix, which is characterized by high tensile strength, resistance to stress corrosion cracking, and improved resistance to pitting. It is used primarily to weld duplex stainless steels, which contain approximately 22 percent Cr such as UNS S31803 and S32205.

TYPICAL CHEMICAL COMPOSITION OF SOLID WIRE:

Element	C	Mn	Si	S	P	Cr	Ni	Mo	N
%	0.020	1.30	0.30	0.020	0.020	22.5	8.5	3.0	0.12

TYPICAL MECHANICAL PROPERTIES OF ALL WELD METAL:

UTS	Elongation
(MPa)	(L = 5d) %
720	25.0

SHIELDING GAS: Argon

CURRENT CONDITIONS: DCEN

WELDING POSITIONS: H, F, VU, OH

PACKING:

STANDARD SIZE: Diameter 1.6 mm, 2.0 mm, 2.4 mm & 3.2 mm in cut lengths of 1000 mm each.

QUANTITY 5 kgs wire put in an air-tight polythene bag and finally packed in a plastic container.
 Identification – AWS code is punched on each wire.

AUTHORISED DISTRIBUTOR - SALES & SERVICE

Head Office: Marn Burn Business Park | Suite No 900A | Block- BP | Salt Lake | Sector - V | Kolkata - 700091 | West Bengal | India

Regd. Office: 161/1 Mahatma Gandhi Road | Suite 83A | 3rd Floor | Kolkata – 700007 | West Bengal | India

info@crossmarketing.co.in | lakhotia.ravi@gmail.com | +91 89816 20042

<https://crossmarketing.co.in/>