

SECHERON 309L

CODIFICATION :

AWS : SFA 5.4 E309L-16
EN ISO : 3581-A E (23 12 L) R 3 2

CHARACTERISTICS AND APPLICATIONS:

- Stainless steel electrode for welding of similar and dissimilar steels.
- The weld deposit displays good corrosion, scaling resistance and crack resistance.
- It meets customer requirements economically.
- It works well with transformer having low OCV also.
- It is ideally suited for welding similar alloys in wrought or cast form.
- It can also be used for welding dissimilar metals, such as joining SS304L to carbon steel, welding the clad side of SS304L clad steels, and applying stainless steel sheet lining to carbon steel shells.

TYPICAL CHEMICAL COMPOSITION OF ALL WELD METAL:

Element :	C	Mn	Si	Cr	Ni	S	P
Percent :	0.035	0.80	0.80	23.0	12.5	0.022	0.025

TYPICAL MECHANICAL PROPERTIES OF ALL WELD METAL:

UTS	Elongation
(MPa)	(L = 5d)%
550	35.0

CURRENT AND PACKING DATA: AC / DC(+)

Size (mm)	:	5x350	4x350	3.15x350	2.5x350
Dia x Length					
Current Range	:	150-180	110-140	80-110	60-80
(Amps)					
Weight/Carton	:	2.0	2.0	2.0	2.0
(kgs)					

APPROVAL: CE

PRECAUTIONS:

- 1 Re-dry the electrodes at 325-375°C for one hour.
- 2 Use short arc, stringer beads and low currents.

AUTHORISED DISTRIBUTOR - SALES & SERVICE

Head Office: Marn Burn Business Park | Suite No 900A | Block- BP | Salt Lake | Sector - V | Kolkata - 700091 | West Bengal | India

Regd. Office: 161/1 Mahatma Gandhi Road | Suite 83A | 3rd Floor | Kolkata - 700007 | West Bengal | India

info@crossmarketing.co.in | lakhotia.ravi@gmail.com | +91 89816 20042

<https://crossmarketing.co.in/>